

## Environmentally Preferred Dielectric Solvent Product Data Sheet

PO Box 9  
Tucker, GA 30084  
800-886-8240 • 770-621-8240  
[www.ecolink.com](http://www.ecolink.com)  
email: [info@ecolink.com](mailto:info@ecolink.com)

### Description

ELECTRON Environmentally Preferred Dielectric Solvent is an exceptional solvent degreaser formulated without chlorinated solvents or other hazardous ingredients. The base for ELECTRON is a unique high-grade oil distillate, which provides its dielectric strength, allowing it to be used safely on all types of electrical apparatus. With its high flash point, ELECTRON provides an unprecedented degree of user safety.

ELECTRON Environmentally Preferred Dielectric Solvent is strong enough to remove grease, fuel oil, carbon and organic resins yet safe on most plastic and rubber surfaces. Unlike other solvents, ELECTRON can be used without extensive protective equipment. Common sense chemical precautions are required.

### Benefits

- Fully evaporative, leaves no residue
- Not a flammable liquid - TCC Flash point above 140°F (60°C)
- High dielectric strength, (ASTM D-877 test procedures to 46,000 volts)
- Contains no water
- No hazardous ingredients as defined by the EPA.
- Contains no OSHA PEL or ACGIH TLV listed ingredients
- No SARA or RCRA listed ingredients

### Applications

Use undiluted. Spray or wipe ELECTRON on surface to be cleaned. Oil, dirt and carbon will flow off surface. If additional cleaning is required, wipe with rag or brush. Since ELECTRON does not dry as rapidly as trichloroethylene, apply a light spray first, allow 5 minutes to work, then follow with a light spray as a rinse, which will push out the now soluble soils. To speed evaporation wipe with a dry rag, use compressed air, or apply Ecolink Hypersolve® as a rinse agent. ELECTRON also works exceptionally well in filtered or unfiltered parts washers.

### Key Physical Characteristics

Property	Test Method	Typical Value
Autoignition Temperature	ASTM E-659	428° F
Boiling Point, (IPB - FBP)	Calculated	349° F
Color, Saybolt	ASTM D-156	+30
Dielectric Strength (volts)	ASTM D-877	46,000
Flash Point, Tag Closed Cup	ASTM D-93	147° F
Kauri-Butanol No.	ASTM D-1133	58
Moisture Content	ASTM D1533B	0.015% max.
Non-Volatile Residue	ASTM D-2369	< 100 ppm
Physical Form	Appearance	Clear liquid
Pounds per Gal, (15.6 C / 60° F)	Calculated	6.53
Pour Point	ASTM D-97	-40° F.
Power Factor, % @ 25° C	ASTM D-924	0.065
Refractive Index, 20C (68° F)	ASTM D-12181	.4385
Solubility in Water (% @ 68° F)	Calculated	<0.10
Specific Gravity, (15.6° C / 60° F)	ASTM D-287	0.8112
Surface Tension, (Dynes/cm @ 25° F)	Calculated	25
Vapor Pressure, (MM HG @ 68° F)	ASTM D-2879	.30 mm Hg
VOC Content	Calculated Less Exempt	810 grams/liter 122 grams/liter

(N.A.= Not Applicable, N.E.= Not Established)

### Safety and Handling Precautions

Precautionary measures: Contains hydrotreated distillate. Always use with adequate ventilation. Avoid vapors. May cause dizziness or headache. Avoid prolonged or repeated exposure to unprotected skin. Do not ingest. Avoid contact with eyes. Treat as combustible material. Keep container closed when not in use. Consult MSDS.

### Packaging

Product Name	Part No.	Packaging	National Stock No.
ELECTRON	0296-55	55 Gal Drum	6850-01-375-5555
ELECTRON	0296-5	5 Gal Pail	6850-01-375-5553
ELECTRON	0296-1	4 x 1 Gal. Case	6850-01-375-5554
ELECTRON-22	049-1	12 x 22 oz Spray	6850-01-371-8049
ELECTRON	0164-1	12 x 1 Pint Case	